

To Whom It May Concern

This copy is being provided for courtesy purposes only, and does not give any person or company other than our named client a right to rely on these results. No warranties, express or implied, including the warranty of due diligence and care mentioned elsewhere, shall extend to any party other than such named client.



Certificate of Quality

Report number : 10901/00014200.3/L/19 Date of sampling : 2019-06-17
Main Object : analysis Place of sampling : Enemed Installation
Report Date : 2019-06-24 Date received : 2019-06-18
Date of issue : 2019-06-24 Date completed : 2019-06-24
Sample object : 2 Sample number : 8343754
Sample type : Sampled
Sample submitted as : ULSD 10 ppm
Marked : Shore tank 2 running after discharge from Santa Pawlina

NAME	METHOD	UNIT	SPECS		RESULT
			Min	Max	
Lubricity Q	ASTM D 6079	micron		460	392
Derived Cetane Number (DCN)	EN 16715	-	51		55.2
Flash point Q	ASTM D 93	°C	55		60.0
Cetane Index	ASTM D 4737	-	46.0		54.8
Copper Strip Corrosion (3 hrs / 50 °C) Q	ASTM D 130	-		1	1B
Sulphur Q	ASTM D 2622	mg/kg		10	5
Density at 15 °C Q	ASTM D 4052	kg/L	0.820	0.845	0.8284
Micro Carbon Residue (10% bot.) Q	ASTM D 4530 / D 86	mass %		0.30	<0.1
Cold Filter Plugging Point Q	IP 309	°C		5	-5
Viscosity at 40°C	ASTM D 445	mm²/s	2.00	4.50	2.631
Ash Q	ASTM D 482	mass %		0.01	0.001
Distillation	ASTM D 86				
Initial boiling point		°C	Report		167.6
10% Recovered		°C	Report		191.7
50% Recovered		°C	Report		269.8
90% Recovered		°C	Report		337.1
95% Recovered		°C		360	356.5
Final boiling point		°C	Report		367.7
Residue		vol %	Report		0.7
Loss		vol %	Report		0.7
Recovered at 250 °C		vol %		65	37.4
Recovered at 350 °C		vol %	85		93.8
Oxidation Stability (**)	ASTM D 2274	g/m³		25	18
FAME (iii)	EN 14078	vol %	Nil		Below 0.05
Water	ASTM E 1064	mg/kg		200	98
Particulate matter	IP 440	mg/kg		24	4

All results in this report refer to the sample(s) tested as taken or submitted like specified in this Analysis report. Uncertainties, available on request, apply in the evaluation of the test results. All tests are conducted according to the latest version of the methods, unless another version is specifically indicated. Where available and for convenience purposes, the tested sample has been checked for compliance with supplied specifications, without accepting any liability. In case of dispute or concern, we refer to the interpretation of test results as defined in ASTM D3244, IP 367, ISO 4259 or GOST 33701. This report shall not be partially copied and reproduced without the written permission of the laboratory.

To Whom It May Concern

This copy is being provided for courtesy purposes only, and does not give any person or company other than our named client a right to rely on these results. No warranties, express or implied, including the warranty of due diligence and care mentioned elsewhere, shall extend to any party other than such named client.



Certificate of Quality

Report number : 10901/00014200.3/L/19 Date of sampling : 2019-06-17
Main Object : analysis Place of sampling : Enemed Installation
Report Date : 2019-06-24 Date received : 2019-06-18
Date of issue : 2019-06-24 Date completed : 2019-06-24
Sample object : 2 Sample number : 8343754
Sample type : Sampled
Sample submitted as : ULSD 10 ppm
Marked : Shore tank 2 running after discharge from Santa Pawlina

NAME	METHOD	UNIT	SPECS		RESULT
			Min	Max	
P.A.H.	IP 391	mass %	11		2.5

Test comments:
Derived Cetane Number (DCN) (EN 16715): Performed By Third Party Laboratory

Lab comments:
The results are referred to the tested sample.

Q Analysis accredited by NAB-MALTA. Testing laboratory Reg No 007.

All tests are reported according to the latest method version available.

If required, estimated expanded uncertainty U with coverage factor=2 corresponding to level of probability of about 95%, can be provided.

Sampling performed according to ASTM D4057-12.

- (*) Climatically dependent specification.
- (**) Tested for 20hrs if FAME is above 2%vol.
- (iii) 'Not detected'or 'below 0.05%' results are also acceptable.

Signed by: Clifton Friggieri - Laboratory Manager
Issued by: Saybolt Malta Ltd
Place and date of issue: Kalafrana - 2019-06-24

All results in this report refer to the sample(s) tested as taken or submitted like specified in this Analysis report. Uncertainties, available on request, apply in the evaluation of the test results. All tests are conducted according to the latest version of the methods, unless another version is specifically indicated. Where available and for convenience purposes, the tested sample has been checked for compliance with supplied specifications, without accepting any liability. In case of dispute or concern, we refer to the interpretation of test results as defined in ASTM D3244, IP 367, ISO 4259 or GOST 33701. This report shall not be partially copied and reproduced without the written permission of the laboratory.